

TITLE OF THE INVENTION

THERMOINSULATING MAT OF MINERAL FIBERS  
WITH RANDOM ORIENTATION

BACKGROUND OF THE INVENTION

Processes for production of thermoinsulating mats or felts of mineral fibers (glass fibers or rock fibers) whose orientation is almost random, as described in European patent 0 133 083, are already known. These products have advantageous qualities, but they have a high density (from 50 to 150 kg/m<sup>3</sup>) and do not have a sufficient flexibility for some applications, in particular for applying such insulating mats to cylindrical surfaces, e.g., of tanks, without forming pockets of condensation on the side in contact with the cylindrical surface and without forming cracks in their outside surface.

SUMMARY OF THE INVENTION

This invention has as an object to provide a product having the qualities required for the above applications.

It has unexpectedly been found that by reducing the diameter of the fibers very appreciably, relative to the known fibers, a product having the desired qualities and a density clearly lower than that of similar known products can be produced.

*double crimped* This invention comprises a thermoinsulating mat of *flexible* mineral fibers having a *substantially* quasi-random orientation in which the great majority of fibers have a diameter between 2.5 and 4.5 micrometers and a length from 2 to 15 cm and in which the mat has a density not greater than 40 kg/m<sup>3</sup>.

#### BRIEF DESCRIPTION OF THE DRAWINGS

By way of example, an embodiment of the mat according to the invention will now be described with reference to the accompanying drawing which shows, by way of example, how the mat according to the invention can be produced. The drawing schematically shows an installation for the production of a thermoinsulating mat of mineral fibers having a quasi-random orientation according to the invention.

#### DESCRIPTION OF THE PREFERRED EMBODIMENT

Known mats of mineral fibers having a quasi-random orientation are formed from glass or rock fibers having a diameter of 6 to 14 micrometers and a length of several centimeters. According to the invention, the mat is formed by much finer mineral fibers having, for the great majority of them, an average diameter of 2.5 to 4.5 micrometers and a length of 2 to 15 cm.

How an insulating mat having the desired qualities indicated above can be produced with such a material will now be described.

The mat or felt of glass fibers (or other mineral fibers) arrives at 1 with nonpolymerized glue thereon and passes, with

Concrete examples of various values (speeds of various conveyors and input and output heights of some conveyors) will now be given.

$$V_{\text{zone IIa}} = \frac{V_r}{\sqrt{V_r/V_c}}$$

The adjustment of the thicknesses of the felt takes place as follows:

Upstream section, zones Ia and IIa

if H'1 is the input height in the conveyor of zone Ia,

if H'2 is the output height of the conveyors of zone IIa,

if Ee is the final thickness of the mat, selected according to the desired apparent density (LAD),

then:

$$H'1 = (1.2 \text{ to } 2.3) \cdot Ee;$$

$$H'2 = (1.3 \text{ to } 2.4) \cdot Ee;$$

Downstream section, zone IIIa;

if H'3 is the input height between conveyors 4 and 4',

if H'4 is the output height between conveyors 4 and 4',

then:

$$H'3 = (1.0 \text{ to } 1.30) \cdot Ee;$$

$$H'4 = (1.0 \text{ to } 1.20) \cdot Ee;$$

Conveyors 3, 3' and 4, 4' oppose an increase in the thickness of the mat under the effect of the axial pressure that it undergoes.

The two sections, upstream (Ia and IIa) and downstream (IIIa), are mechanically connected to one another and are placed on a traveling path making possible the positioning of their unit relative to the oven.

Each conveyor is equipped with a conveyor belt driven by a dc geared motor unit making possible a precise adjustment of the speeds to the desired values.

SECRET " T 686 T 450

Thanks to the fineness of the fibers and to the completely random arrangement of the insulation fibers in the finished product, the latter has a compact surface, a good flexibility and a constant thickness with good insulation qualities.

The application of the product to large plane or nonplane (concave or convex) surfaces is easy. The product offers a resistance to compression which is sufficient to make it possible to apply on it a protective coating or a layer of additional insulation. The product can be in the form of a felt roll, lending itself well to the application to the outside face of a fire-resistant coating and to cylindrical surfaces.

The product thus obtained exhibits the following characteristics:

- random or quasi-random distribution of the fibers (glass or rock fibers),
- great fineness of the fibers (diameters of 2.5 to 4.5 micrometers),
- length of the fibers of 2 to 15 cm,
- apparent density (LAD) less than or equal to  $40 \text{ kg/m}^3$ ,
- resistance to compression (for a crushing of 10%) greater than or equal to  $0.5 \text{ kN/m}^2$ ,
- heat conductivity coefficient less than or equal to  $0.040 \text{ W/mK}$ .

The final mat can have a thickness of 20 to 200 mm.

The mat can have a further surfacing, i.e., it can be coated with one or two adherent sheets of paper, aluminum, polyethylene or PVC.

The random distribution of the fine fibers used assures, during the winding of the mat around a cylindrical surface, that this winding is performed without deformation of the inside and outside surfaces, which are thus perfectly cylindrical with good application on the element to be insulated, avoiding any pockets of condensation of the inner side and any cracks of the outer side.

558401-1685463